

Einsatzempfehlung

Material	Stahl N/mm ²				Rostfreie Stähle		Guss		NE-Metalle			Superleg.		Stahl gehärtet	
Zugfestigkeit	<500	<800	<1200 (<HRC38)	<1600 (<HRC48)	<800	<1200	GG	GGG	Al Knetleg.	Al Si<10%	Cu, Ms	Ti/Ni/Co <900	900-1500	HRC 48-57	HRC 58-63
40 00 601 368 - Vc (m/min)	30	28	8	4	7	7	15	18	35		60	7	6		
40 00 601 464 - Vc (m/min)	25								40	40					
40 00 601 473 - Vc (m/min)	60	60	45	30	24	20	45	35	180	80	180	18	16	8	6
Kühlung	Emulsion	Emulsion	Emulsion	Schneidöl	Schneidöl	Schneidöl	Emulsion	Emulsion	Emulsion		Emulsion	Schneidöl	Schneidöl		